

# TEST 727

## soft PVC covered in a aluminium gel coat

**generally:**

<b>according:</b>	ISO 15701:2015 / VSLIC C-4420 / IUF 442
<b>suitable:</b>	For determining the migration fastness against soft PVC
<b>durability:</b>	5 years (minimum)
<b>storing conditions:</b>	must be well packed and kept dark

**specification of material:**

<b>article 727</b>	soft PVC	
<b>base material</b>	Polyvinylchloride	(48.0 ± 1.0) %
	Plasticisers	(48.0 ± 1.0) %
	Stabiliser	about 1 %
	Titanium dioxide	about 3 %
<b>cover material</b>	Aluminium gel to prevent volatilisation of the plasticiser.	

**batch control:**

<b>silver gel coat</b>	approved
<b>thickness of PVC</b>	0.5 mm
<b>behaviour of migration</b>	approved